

Product Data



BLAKES HARD RACING WHITE

76300

HSE Number 6969

Description: BLAKES HARD RACING antifouling is a high strength burnishable antifouling especially for power boats, racing yachts and vessels moored in a mud berth may also be used on vessels that are dry sailed. For use below the waterline.

Recommended use: Suitable for all substrates except aluminium. Risk of corrosion in case of direct contact.

Availability: Subject to confirmation.

PHYSICAL CONSTANTS:

Colours/Shade nos: White/10000
Finish: Flat
Volume solids, %: 56 ± 1
Theoretical spreading rate: 13.5 m²/litre - 40 micron
Flash point: 39°C/102°F
Specific gravity: 1.4 kg/litre - 11.7 lbs/US gallon
Dry to touch: 4 (app) hours at 20°C/68°F
8 (app) hours at 10°C/50°F
V.O.C.: 395 g/litre - 3.5 lbs/US gallon

The physical constants stated are nominal data according to the BLAKES Group's approved formulas. They are subject to normal manufacturing tolerances and where stated, being standard deviation according to ISO 3534-1. Further reference is made to "Explanatory Notes" in the BLAKES PAINT MANUAL.

APPLICATION DETAILS:

Application method: Airless Spray Air Spray Brush/Roller/Paint pad
Thinner (max.vol.): BLAKES THINNERS No 3 (5%) BLAKES THINNERS No 3 (5%) BLAKES THINNERS No 3 (5%)
Nozzle orifice: .018" - .023"
Nozzle pressure: 150 bar/2175 psi
(Airless spray data are indicative and subject to adjustment)
Cleaning of tools: BLAKES THINNERS No 3
Indicated film thickness, dry: 40 micron/1.6 mils
Indicated film thickness, wet: 75 micron/3 mils
Recoat interval, min. 5 hours (20°C/68°F)
9 hours (10°C/50°F)
Recoat interval, max. None (See REMARKS overleaf)

Safety: Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult BLAKES PAINTS Material Safety Data Sheets and follow all local or national safety regulations. Avoid inhalation, avoid contact with skin and eyes, and do not swallow. Take precautions against possible risks of fire or explosions as well as protection of the environment. Apply only in well ventilated areas.

Always read the label. Use pesticides safely

Issued: NOVEMBER 2002

2. BLAKES HARD RACING WHITE

SURFACE

PREPARATION: **Existing antifouling:** Remove possible oil and grease, etc, with a suitable detergent BLAKES SURFACE CLEANER followed by (high pressure) fresh water cleaning, also to remove any loose or flaking leached antifouling. Allow the surface to dry before recoating. Whether or not to use a sealer coat depends on the type and condition of the existing antifouling.

APPLICATION

CONDITIONS: The surface must be completely clean and dry. Application should only take place in dry weather and the temperature of the surface should be above the dew point to avoid condensation. The temperature of the paint itself should be above 15°C/59°F. Avoid direct sunlight. In confined spaces provide adequate ventilation during application and drying.

PRECEDING COAT: BLAKES UNDERWATER PRIMER, BLAKES KEEL PRIME, BLAKES EPOXY PRIMER UNDERCOAT or according to specification.

SUBSEQUENT COAT: None.

REMARKS:

Stir well before use as the product contains heavy particles.
Keep thinning to a minimum to ensure that correct film thickness is obtained.
2-3 coats recommended.
When applied by roller, paint pad or air spray an extra coat may be necessary to ensure correct film thickness.
Airless spray application: minimum 120 micron total dry film thickness.
Launching not before 24 hours after application of last coat. BLAKES HARD RACING WHITE can be left out of water for up to 3 months after painting.
If a new coat of BLAKES HARD RACING WHITE is applied after prolonged exposure to polluted atmosphere remove accumulated contamination by fresh water hosing and allow surface to dry

before painting.

Note: **Only HARD RACINGS with the same product no. - 76300 - should be mixed.**
The information given in the Technical Data Sheet is intended for commercial use.

ISSUED: NOVEMBER 2002 - 7630019990CR008
BLAKES PAINTS

This Product Data Sheet supersedes those previously issued. For definition and scope, see explanatory notes to applicable Product Data Sheets.

Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User. The Products are supplied and all technical assistance is given subject to BLAKES PAINTS GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise.

Product data are subject to change without notice and become void five years from the date of issue.